

Eclipse Data Sheet



Primary Color(s)	Charcoal, Black, White
Stone Type	Marble Thickness 0.5" - .75"
Finish	Split Face Country China
Variation	Medium
Sizes	Flat Panels - 6" x 24" Corner - 6" x 18" X 6"
Item Codes	6" x 24" - V0624-100-EE-LF 6" x 18" - V0618-100-EE-LC
Packaging	Panels: 6 pcs / box; 210 pcs/crate Corners: 4 pcs/box; 80pcs/crate
Application	Walls, barbeque areas, etc
Technical Info	Average Compressive Strength: Dry/4000 Psi

Adhesive	Exterior Application	Exterior application: a flexible latex based mortar system suitable for the stone is recommended.
	Interior Application	Interior application: a thin set mortar suitable for the stone is recommended. ** For light colored stones, a white mortar is recommended.
Substrates	Exterior / Interior	<ul style="list-style-type: none"> • Fully cured concrete (at least 28 days cured) • Masonry brick • Regular brick • Cement mortars • Cementitious backer units
	Interior Only	<ul style="list-style-type: none"> • Gypsum plaster (max 10' high) • Gypsum wallboard (max 10' high) • Exterior grade plywood (max 10' high) • Cementitious backer units